

**FUEL CELL USING BIOFILMS AS CATALYST FOR THE CATHODE  
REACTION AND/OR THE ANODE REACTION**

**DESCRIPTION**

5

**Technical Field**

The present invention relates to a process for the treatment of a fuel cell electrode (cathode and/or anode), the said treatment being intended to improve the catalysis of the reaction at the electrode, and to a fuel cell provided with a biofilm on at least part of the surface of the said electrode.

The general field of the invention is therefore that of fuel cells and more particularly that of the catalysis of the reactions at the electrodes of fuel cells.

**Prior Art**


20

The basic principle covering the operation of a fuel cell, for example a hydrogen/air fuel cell, is the electrochemical combustion of dihydrogen ( $H_2$ ) and dioxygen ( $O_2$ ).

25


The reactions at the terminals of the electrodes are represented by the following equations (1) and (2):

(1) at the anode:



30

(2) at the cathode:



These two reactions have slow rates, resulting in catalysts being placed at the electrodes so as to

improve the rate of the reactions taking place at the surface of these electrodes.

5 Generally speaking, the catalysts placed so as to improve the rate of the electrode reactions are metal catalysts, such as catalysts based on platinum or gold.

However, the use of such catalysts has the following drawbacks:

- 10 - they constitute products that are both expensive, because of the amounts needed to obtain satisfactory catalysis, and potential pollutants of the environment; and
- 15 - they have a low efficiency at low temperatures, such as room temperature, which may lead to cell start-up difficulties.

20 To alleviate these drawbacks, research has been carried out into putting in place less expensive and more efficient catalysts.

25 Thus, as regards cells operating by gas diffusion, research has been carried out essentially into metal catalysts that are less expensive than platinum or gold or into novel arrangements or combinations of metal catalysts, that may contribute to improving the catalysis of the electrode reactions. However, the pollution problem inherent in the use of this type of catalyst still remains.

30

As regards fuel cells operating in aqueous medium, research has been carried out into the incorporation of specific bacteria or enzymes at the electrodes by grafting.

35

However, the cells of the prior art generally use specific bacteria for providing functions other than that of improving the catalysis of the electrode reactions.

5  
Thus, the presence of bacteria at the electrodes may prove to be effective for producing or regenerating, within the core of the cell, the fuel, such as hydrogen, that is oxidized at the anode. Many examples  
10 of bacteria providing this function are given in an article by Palmore and Whitesides, "Microbial and Enzymatic Biofuel Cell", American Chemical Society, Chapter 14, pages 271-290 (1994) [1]. In other cases, bacteria may also be used to regenerate the reduced  
15 form of an electrochemical mediator, responsible for ensuring electron transfer at the anode. To reduce the electrochemical mediator, specific bacteria extract electrons from substrates, such as glucose, sucrose, succinate. Many examples of bacteria of this type are  
20 cited in the abovementioned reference [1]. From among the most recent studies there may be cited the study mentioned in the article by Yagishita et al., "Behaviour of glucose degradation in *Synechocystis* sp.M-203 in bioelectrochemical fuel cells",  
25 Bioelectrochemistry and Bioenergetics, 1997, Vol. 43, 177-180 [2] that describes a cell using cyanobacteria to reduce the compound 2-hydroxy-1,4-naphthoquinone which serves as electrochemical mediator for electron transfer at the anode. The article by Cooney et al.,  
30 "Physiologic studies with sulphate-reducing bacterium *Desulfovibrio desulfuricans*: evaluation for use in a biofuel cell", Enzyme and Microbial Technology, 1996, Vol. 18, pages 358-365 [3], mentions a cell employing sulphate-reducing bacteria to regenerate the sulphide  
35 ion that is reduced to sulphate at the anode.

However, the performance of such cells remains insufficient. In addition, the use of microorganisms in the abovementioned fuel cells does not contribute to the improvement in the electrochemical rates at the electrodes, but to the biological production of fuel or to the regeneration of a mediator compound. Consequently, it will still be necessary, for these constructions, to use catalysts on the electrodes, and in particular on the anodes in the case of the examples mentioned, so as to accelerate electron transfer between the fuel and the electrode or, where appropriate, between the electrochemical mediator and the electrode.

Attempts using isolated specific enzymes, such as oxidoreductases, to improve the reaction rates at the electrodes have been explored in the prior art.

Thus, the authors E. Katz et al., in the article "A biofuel cell based on two immiscible solvents and glucose oxidase and microperoxidase-11 monolayer-functionalized electrodes", New Journal of Chemistry, 1999, 481-487 [4], propose the use of the enzyme glucose oxidase to catalyse, on the anode side, the oxidation of glucose used as fuel and the enzyme microperoxidase-11 to catalyse the reduction of cumene peroxide taken as oxidizing agent.

However, although these studies are aimed at improving the rates at the electrodes, and particularly at the cathode, they make use of relatively expensive enzymes and sometimes of additional organic compounds that act as electrochemical mediators to ensure electron transfer between the active site of the enzyme and the

electrode. They may also require the use of sophisticated chemical techniques so as to graft suitable enzymes onto the surface of the said electrodes. In the current situation, this kind of cell  
5 may be used only for very targeted types of application requiring only low power levels and having no cost constraint.

Finally, the authors Hasvold et al. in the article  
10 "Sea-water battery for subsea control systems", Journal of Power Sources, 65, pages 253-261, 1997 [5], relating to a study of batteries with a soluble anode operating in a marine environment, observed that batteries immersed in seawater had a higher efficiency than those  
15 operating in the open air. They deduced from this that the improvement in performance was due to the spontaneous formation of a biofilm during operation of the cell (the term "biofilm" denoting a film comprising a set of microorganisms deposited spontaneously on a  
20 surface, the said microorganisms deriving from biological water, such as seawater, river water, etc.) particularly on the surface of the cathode, which is thought to be responsible for improving the oxygen reduction catalysis. These observations stem in  
25 particular from the studies carried out on the biocorrosion of materials exposed to biological water, such as seawater or river water. These studies have demonstrated that the growth of biofilms leads to an increase in the corrosion potential of these materials,  
30 due to an increase in the cathode reaction rate of the corrosion phenomenon.

However, the role of biofilms in improving the operating performance of a battery, especially in the  
35 Hasvold publication "Sea-water battery for subsea

control systems", Journal of Power Sources, 65, pages 253-261, 1997 [5], mentioned above, is dealt with as a contingent phenomenon taking place during operation of the battery, or even as a phenomenon hampering proper operation of the battery, when the biofilm assumes excessively large proportions and consequently impedes the accessibility of the reactants at the cathode. Furthermore, that document does not present specific techniques for promoting and optimizing the growth of the biofilm so as to improve the performance of the battery.

There is therefore at the present time a real need for improving the catalysis of electrode reactions, especially the cathode reaction, which situation constitutes a limitation for the proper operation of a fuel cell.

#### **Summary of the Invention**

To do this, the object of the present invention is specifically to propose a process for the treatment of an electrode of a fuel cell, before the said cell is operated, the said method having the result of improving the catalysis of the reaction at the electrode in question.

According to the invention, this result is achieved by a process for the treatment of at least one of the electrodes (cathode and/or anode) of a fuel cell, before the said cell is operated and before or after the said electrode is placed in the said cell, consisting in forming a biofilm on at least part of the surface of the said electrode, by immersing the said electrode in a medium capable of causing the growth of

biofilms, the said biofilm being intended to catalyse the reaction at the electrode, and consisting simultaneously in subjecting the said electrode to a bias potential.

5

The present invention thus provides a process for the treatment of an electrode (cathode and/or anode) of a fuel cell, prior to the operation of the said cell, during which treatment a biofilm is deposited on at least part of the surface of the said electrode, this biofilm attaching naturally to the surface of the electrode, without requiring particular techniques. This biofilm is intended to act as catalyst for the reactions at the electrode (that is to say the oxidation reaction at the anode and the reduction reaction at the cathode) when the cell is operated after the treatment process according to the present invention. Catalysis of the reactions at the electrodes is achieved by depositing a biofilm on the surface of the electrodes, because the biofilms are capable of spontaneously manufacturing the elements needed for catalysing the electrode reactions.

Thus, the formation of the biofilm for catalysing the electrode (anode or cathode) reactions makes it possible to limit, or even to completely replace, the charging with mineral catalysts and also to replace the materials normally used to make the cathode, such as graphite and platinum, with less expensive materials, such as stainless steels and aluminium, nickel or titanium alloys.

In addition, given that the biofilm synthesizes the elements needed for catalysing the reaction at the electrodes, it is no longer necessary, in the

construction of the cell, to add, in the electrode compartments, organic, mineral or biological compounds, as is the case with cells based on the principle of enzyme catalysis.

5

In addition, the process according to the invention includes, concomitantly with the formation of the biofilm, a step intended to optimize the quality of the biofilm deposited. This step consists in subjecting at least one of the electrodes, which is immersed in a medium capable of causing the growth of biofilms, to a bias potential. This bias potential may be fixed or may vary and is applied for a suitable time. It is defined with respect to a reference electrode. The suitable time for which this potential is applied may be determined in the following manner:

- during the biasing phase, a curve  $i = f(t)$ , corresponding to the current delivered by the electrode as a function of time, is established; and
- as soon as the sigmoid-shaped  $i = f(t)$  curve exhibits the start of a plateau, the application of the potential may be stopped, the appearance of a plateau in the curve meaning that the surface of the cathode is optimally covered with a biofilm. The cathode is thus ready to be used, optimally, without any other conditioning being necessary.

Of course, the time for which the bias potential is applied to the cathode, when immersed in a suitable medium, may be less than that mentioned above (that is to say less than the time needed to obtain the onset of a plateau) or greater than it.

The treatment process according to the invention is therefore particularly beneficial insofar as it makes



it possible to obtain an electrode completely or partly covered by a biofilm of optimum quality, the said biofilm being capable, during operation of the cell, of instantly catalysing the electrode reaction without any start-up difficulty.

It should be noted that, according to the invention, the process for the treatment of at least one of the electrodes may be carried out when the electrode has not yet been placed in a fuel cell device ("before the said electrode is placed in the said cell") or when the electrode has already been placed in a fuel cell device ("after the said electrode is placed in the said cell"). However, for both these situations, the treatment process according to the invention will always be carried out before the cell is put into operation.

A distinction may be made, through this treatment process according to the invention, from the embodiments of the prior art that mentioned the existence of biofilms in the operation of a battery by the fact that, in these embodiments, the biofilm formed at the surface of the electrodes during the operation of the batteries (the formation of the biofilm then being considered as an artefact and a phenomenon contingent on the operation of the battery), whereas within the context of our invention the biofilm is formed before the cell is put into operation and has optimum catalytic properties thanks to the biasing step.

Particularly when the electrode is a cathode, the bias potential imposed on the said cathode within the context of the treatment process of the invention must, preferably, correspond to an optimum value. In other words, this bias potential must be as cathodic as

possible, as in this way the cathode treatment process will be more rapid and the currents obtained will be higher (that is to say the current delivered by the cell during its operation will be higher), but this potential must not, however, be too cathodic so as to have a high enough potential difference delivered by the cell during its operation. The optimum bias potential to be applied to the cathode, complying with the abovementioned compromise, may be easily chosen by those skilled in the art.

Advantageously, bias potentials ranging from -0.5 to 0.0 V with respect to a saturated calomel reference electrode (SCE) will be used for treating a cathode according to the process of the invention.

In accordance with the invention, the electrode intended to be treated is immersed in a medium capable of causing the growth of biofilms. In other words, such a medium is a medium containing a set of microorganisms, the said microorganisms being capable of growing on a support, such as an electrode as in the present case.

The medium capable of causing the growth of biofilms, used to form, during the treatment process, the biofilm on at least part of the surface of an electrode, may be of any type and may be chosen from natural water, such as river water, well water, industrial water, that is to say unsterilized water used in industry, for example to cool plants, seawater or water derived from a culture medium. It should be noted that, according to the invention, a culture medium is a medium to which nutrients necessary for effective growth of the

microorganisms contained in the said medium have been added.

5 Preferably, the medium capable of causing the growth of a biofilm is seawater, the said seawater being particularized by the fact that it contains a fauna of microorganisms that is varied and therefore particularly suitable for forming high-quality biofilms.

10 Also preferably, the medium capable of causing the growth of biofilms is a circulating medium, the said medium, thanks to its continuous replenishment, thus making it possible to replenish the biological fauna  
15 continuously and, consequently, to improve the quality of the biofilm being deposited on the surface of the electrode during the said process.

20 Another object of the present invention is to propose a fuel cell comprising at least one cell having an anode compartment supplied with an oxidizing agent, the said compartment including an anode, and the said cell having a cathode compartment supplied with a reducing agent, the said compartment including a cathode, the  
25 said compartments being placed on either side of a membrane, characterized in that at least one of the electrodes (anode and/or cathode), prior to the operation of the said cell, is coated on at least part of its surface with a biofilm intended to catalyse the  
30 reaction at the electrode.

Preferably, the biofilm is deposited on at least part of the surface of at least one of the electrodes by implementing the treatment process as described above.  
35

Apart from the benefit, already mentioned, of using a biofilm to catalyse the electrode reaction, the fact of depositing a biofilm on at least one of the electrodes (cathode or anode), before the fuel cell is put into  
5 operation, makes it possible to offset the slow start of the electrode reaction, which would be the case if the electrode reactions were, among others, catalysed by a biofilm deposited during the operation of the cell. However, it is preferable and necessary, for  
10 efficient start-up of the reaction, for the material of the electrode to be a material that is active in the catalysis of the electrode reaction. In other words, it is preferable for the electrode to include, in addition to the biofilm deposited on its surface, metal  
15 catalysts based on precious or semi-precious metals, such as platinum or rhodium, or complexes that include such metals.

According to the invention, when only one of the  
20 electrodes, in particular the cathode, has a biofilm on its surface, deposited before the cell is put into operation, the other electrode may include, for example, catalysts of any type, such as mineral catalysts, for example catalysts based on platinum or  
25 on platinum group metals.

However, the anode reaction is preferably catalysed, within the context of this invention, by a suitable biofilm (that is to say a biofilm intended to catalyse  
30 the anode reaction) deposited on at least part of the surface of the anode. For example, this biofilm will comprise microorganisms that can produce metabolites capable of increasing the anode reaction rate. It should be noted that the biofilm may be deposited on

the surface of the anode by a treatment process according to the invention.

5 The present invention applies to fuel cells operating in aqueous medium. For this type of operation, the anode and cathode compartments are filled with water, in which an anode and a cathode are respectively immersed and into which, in the respective compartments, a stream of oxidizing agent and a stream  
10 of reducing agent are sparged. Preferably the water filling the anode and cathode compartments is water capable of regenerating the biofilm deposited on at least part of the surface of the cathode and optionally of the anode before the cell is put into operation.  
15 Preferably, the water filling the anode and cathode compartments is circulating water.

The present invention also applies to cells operating by gas diffusion. For this type of operation, the  
20 oxidizing agent and the reducing agent feed their respective compartments directly in the form of a gas stream. However, it should be noted that, for a cell whose cathode reaction and possibly whose anode reaction are catalysed by a biofilm, it is necessary to  
25 ensure a moisture content suitable for the survival and replenishment of the biofilm, it being possible for this moisture content to be controlled:

- either by controlling the moisture content of the gases entering the cell, that is to say that the gas  
30 stream or streams feeding the compartment or compartments provided with a biofilm will preferably have a moisture content such that it allows the said biofilm to be regenerated;

- or by providing a stream of water coexisting in  
35 parallel with the gas stream or streams feeding the

compartment or compartments provided with a biofilm, the said stream of water being intended to regenerate the said biofilm;

- or else by the water produced by the reaction,  
5 when the cell is a hydrogen/oxygen cell.

Finally, the fact that the cathode and/or anode reaction can be catalysed according to the present invention by a biofilm deposited on at least part of  
10 the surface of the cathode and/or of the anode allows the use of cathode and/or anode constituent materials that are less expensive than those used in the prior art.

Thus, advantageously, the electrode (anode or cathode)  
15 may be formed from a material chosen from the group comprising stainless steel and aluminium, nickel or titanium alloys.

The present invention may apply to any type of fuel  
20 cell, in particular to cells whose oxidizing agent is oxygen and whose reducing agent is hydrogen.

The subject of the present invention is also an electrode (anode and/or cathode) coated on at least  
25 part of its surface with a biofilm, before it is placed in the said cell.

The biofilm is preferably deposited on at least part of the surface of the said cathode by the treatment  
30 process as described above.

This electrode (anode and/or cathode) is preferably held in a medium capable of regenerating the biofilm, so as to ensure the survival of the said biofilm.  
35

Other advantages will become more clearly apparent on reading the description that follows, given of course by way of illustration but implying no limitation, with reference to the appended drawings.

5

#### **Brief Description of the Drawings**

Figure 1 shows schematically, in vertical cross section, a hydrogen/oxygen fuel cell operating in aqueous medium, the cathode reaction of which is catalysed by a biofilm deposited on at least part of the surface of the cathode before the said cell is put into operation.

Figure 2 shows schematically, in vertical cross section, a proton exchange membrane cell with gas diffusion.

Figure 3 shows schematically, in vertical cross section, a cell operating in aqueous medium used to implement the present invention.

#### **Detailed Presentation of Methods of Implementation**

Figure 1 shows schematically a hydrogen/oxygen cell operating in aqueous medium, the cathode reaction of which is catalysed by a biofilm.

This figure shows that the cell comprises in succession a cathode compartment 1 and an anode compartment 3, the said compartments being placed on either side of a semi-permeable membrane 5. The two compartments contain water, in which the suitable electrodes, that is to say the cathode 7 in the case of the cathode compartment 1 and the anode 6 in the case of the anode compartment 3,

- are immersed. The water filling in particular the cathode compartment is biological water, as defined above. The cathode compartment 1 is provided with an oxygen inlet 9, the said oxygen being sparged into the water in the said compartment. In this compartment, the oxygen is reduced to hydroxyl ions  $\text{OH}^-$ , according to the equation  $\text{O}_2 + 2\text{H}_2\text{O} + 4\text{e}^- \rightarrow 4\text{OH}^-$ , the said ions  $\text{OH}^-$  passing through the semi-permeable membrane in the direction of the anode compartment. According to the invention, the cathode reduction reaction is catalysed by the presence of a biofilm 11 deposited on at least part of the surface of the cathode before the cell is put into operation.
- The anode compartment 3 is in turn provided with a hydrogen inlet 13, the said hydrogen being sparged into the biological water. In this compartment, the hydrogen is oxidized to water, according to the equation  $2\text{H}_2 + 4\text{OH}^- \rightarrow 4\text{H}_2\text{O} + 4\text{e}^-$ .
- Preferably, the biological water present in the cathode compartment is regularly replenished so as to maintain the optimum characteristics of the biofilm during operation of the cell.
- Figure 2 shows a schematic view of a cell of a hydrogen/oxygen fuel cell according to the invention, operating by gas diffusion. This cell comprises, in succession, a cathode compartment 15 and an anode compartment 17 placed on either side of a proton exchange membrane 19.
- The cathode compartment comprises a porous cathode 21, an oxygen gas supply system 23 and a biofilm 25, acting as catalyst, located between the cathode and the



membrane. The biofilm 25 is shown in the form of beads. According to the invention, the cathode, before the cell is put into operation, is subjected, while immersed in biological water as described above, to a bias potential for a predetermined time, thus making it possible to optimize the catalytic properties of the biofilm deposited on the surface of the cathode. It should be noted that, to ensure correct operation of such a cell, the cathode reaction of which is catalysed by a biofilm, it is necessary to ensure an adequate moisture content for the survival and replenishment of the biofilm, it being possible for this moisture content to be controlled either by controlling the moisture content of the gases entering the cell, or by providing a water flow system in parallel, or else by the water produced by the reaction in the case of a hydrogen/oxygen cell.

The anode compartment comprises a porous anode 27, a hydrogen supply system 29 and a catalytic layer 30, also shown in the form of beads. This catalytic layer may be made from all types of catalytic materials, such as metals (platinum or platinum group metals), or else from a suitable biofilm (that is to say one capable, in this case, of catalysing the oxidation of hydrogen).

The invention will now be described in relation to the examples given below.

The examples below use a fuel cell operating in aqueous medium, like the one shown in Figure 3.

The anode compartment 31 and the cathode compartment 33 are separated by a Nafion-type proton exchange membrane 35. Two streams of water 37 and 38 flowing from tanks

- 39 into the cathode compartment 33 and into the anode compartment 31, respectively, are enriched with a sparge 41 of dihydrogen into the anode compartment 31 and a sparge 43 of air into the cathode compartment 33.
- 5 It should be noted that the stream of water 37 is a stream of biological water intended to ensure effective continuous regeneration of the biofilm deposited on at least part of the surface of the cathode.
- 10 The anode 45 is formed from a 30 cm<sup>2</sup> platinum mesh and the cathode 47 is formed from a stainless steel plate covered with a biofilm 49. The anode 45 and the cathode 47 are electrically connected via a resistor 57 of variable resistance. Outlets 51 are provided at the
- 15 tanks 39 so that they are replenished with water, especially on the cathode side.

The anode and cathode compartments are held together by clamping, gaskets 53 between the two compartments

20 providing a sealing action. These gaskets are manufactured by cutting them from rubber sheets. One of these gaskets is placed directly against the stainless steel cathode. An open window 55 cut at the centre of the sheet makes it possible to precisely define the

25 working surface of the cathode employed in the operation of the cell.

Prior to being placed in the cell as described above, the stainless steel cathode 47, having dimensions of

30 100 × 100 × 2 mm in the particular case of these examples, is immersed in circulating seawater and held for several days at a fixed bias potential  $E_{\text{bias}}$  expressed with respect to the saturated calomel reference electrode (SCE) so as to bias the said

35 cathode, the said bias being intended to optimize the

catalytic oxygen reduction properties of the biofilm deposited. After this preliminary step, the cathode is inserted into the cell. At the end of the tests, the cell is removed and the cathode is cleaned with  
5 mechanical means and then with a sodium hypochlorite solution, and finally rinsed with seawater. It is then put back into the cell in the same configuration as previously and the characteristics of the cell are again tested under such conditions.

10

The examples below illustrate the results obtained for a cell with the configuration described above, the said cell being subjected to various bias conditions (potential and duration) before the cell is put into  
15 operation. For each of these examples, the ratio of the power delivered with a biofilm (first series of tests) to the power delivered without a biofilm (second series of tests) on the cathode was measured for various electrical resistance values.

20

#### Example 1

The characteristics of the first series of tests were the following:

- 25
- conditioning potential: -0.10 V/SCE;
  - conditioning time: 15 days;
  - fluid circulating on the cathode side: seawater;
  - fluid circulating on the anode side: seawater;
  - working area of the cathode: 9 cm<sup>2</sup>.

30

It should be noted that the cathode was a plate of 316 L stainless steel having the dimensions of 100 × 100 mm.

Table 1 below gives the variation in the current during the cathode treatment process according to the invention.

5

TABLE 1

Duration (in days)	0	4	6	8	10	10
Current (in mA)	0.1	0.4	2.0	7.5	10.3	9.2

10 In this first series of tests, the power delivered by the cell was measured for various electrical resistance values.

15 In a second series of tests, the power delivered by the cell was measured for various electrical resistance values, the cell not having a biofilm on the cathode and not having undergone the conditioning step.

The (power with biofilm/power without biofilm) ratios are given in Table 2 below.

20

TABLE 2

Resistance (in $\Omega$ )	1	10	100	1000	$10^4$	$10^5$	$10^6$
Ratio	34	31	29	21	30	7	4

Example 2

25 The characteristics of the first series of tests were the following:

- conditioning potential: -0.10 V/SCE;
- conditioning time: 15 days;

- fluid circulating on the cathode side: seawater;
- fluid circulating on the anode side: distilled water + NaOH (pH = 12.5);
- working area of the cathode: 9 cm<sup>2</sup>.

5

The current values recorded as a function of time were identical to those shown in Example 1.

10 In this first series of tests, the power delivered by the cell was measured for various electrical resistance values.

15 In a second series of tests, the power delivered by the cell was measured for various electrical resistance values, the cell not having a biofilm on the cathode and not having undergone the conditioning step.

The (power with biofilm/power without biofilm) ratios are given in Table 2 below.

20

TABLE 2

Resistance (in $\Omega$ )	1	10	100	1000	10 <sup>4</sup>	10 <sup>5</sup>	10 <sup>6</sup>
Ratio	86	81	81	103	-	24	-

Example 3

25

The characteristics of the first series of tests were the following:

- conditioning potential: -0.30 V/SCE;
- conditioning time: 17 days;
- 30 - fluid circulating on the cathode side: seawater;
- fluid circulating on the anode side: distilled water + NaOH (pH base = 2.3);

- working area of the cathode:  $1.8 \text{ cm}^2$ .

In this first series of tests, the power delivered by the cell was measured for various electrical resistance values.

In a second series of tests, the power delivered by the cell was measured for various electrical resistance values, the cell not having a biofilm on the cathode and not having undergone the conditioning step.

The (power with biofilm/power without biofilm) ratios are given in Table 3 below.

15

TABLE 3

Resistance (in $\Omega$ )	1	10	100	1000	$10^4$	$10^5$	$10^6$
Ratio	79	85	84	51	10	5	4

It may be seen that, for the three examples, the presence of a biofilm deposited on at least part of the surface of the cathode before it is placed in the cell considerably increases the power delivered by the cell having this biofilm.

## References cited

- 5 [1] Palmore and Whitesides, "Microbial and Enzymatic Biofuel Cell", American Chemical Society, Chapter 14, pages 271-290 (1994);
- 10 [2] E. Katz et al., "A biofuel cell based on two immiscible solvents and glucose oxidase and microperoxidase-11 monolayer-functionalized electrodes", New Journal of Chemistry, 1999, 481-487;
- 15 [3] Cooney et al., "Physiologic studies with sulfate-reducing bacterium *Desulfovibrio desulfuricans*: evaluation for use in a biofuel cell", Enzyme and Microbial Technology, 1996, Vol.18, pages 358-365;
- 20 [4] E. Katz et al., in the article "A biofuel cell based on two immiscible solvents and glucose oxidase and microperoxidase-11 monolayer-functionalized electrodes", New Journal of Chemistry, 1999, 481-487; and
- 25 [5] Hasvold et al., in the article "Sea-water battery for subsea control systems", Journal of Power Sources, 65, pages 253-261, 1997.

**CLAIMS**

1. Process for the treatment of at least one of the electrodes (cathode and/or anode) of a fuel cell,  
5 before the said cell is operated and before or after the said electrode is placed in the said cell, consisting in forming a biofilm on at least part of the surface of the said electrode, by immersing the said electrode in a medium capable of causing the growth of  
10 biofilms, the said biofilm being intended to catalyse the reaction at the electrode, and consisting simultaneously in subjecting the said electrode to a bias potential.
- 15 2. Treatment process according to Claim 1, in which the medium capable of causing the growth of biofilms is chosen from:
  - natural water, such as river water, well water or seawater;
  - 20 - industrial water, and water derived from a culture medium.
3. Treatment process according to Claim 2, in which  
25 the medium capable of causing the growth of biofilms is seawater.
4. Treatment process according to any one of Claims 1 to 3, in which the medium capable of causing the growth of biofilms is a circulating medium.  
30
5. Treatment process according to any one of Claims 1 to 4, in which the electrode is a cathode.
6. Process according to Claim 5, in which the bias  
35 potential applied to the cathode has a value ranging



from -0.5 V to 0.0 V with respect to a saturated calomel reference electrode (SCE).

7. Fuel cell comprising at least one cell having an anode compartment supplied with an oxidizing agent, the said compartment including an anode, and the said cell having a cathode compartment supplied with a reducing agent, the said compartment including a cathode, the said compartments being placed on either side of a membrane, characterized in that at least one of the electrodes (anode and/or cathode), prior to the operation of the cell, is coated on at least part of its surface with a biofilm intended to catalyse the reaction at the electrode.

15

8. Fuel cell according to Claim 7, characterized in that the biofilm coating at least part of the surface of the said electrode is obtained by implementing the process according to any one of Claims 1 to 6.

20

9. Fuel cell according to Claim 7 or 8, characterized in that the anode and cathode compartments are filled with water, in which an anode and a cathode are respectively immersed and into which, in the respective compartments, a stream of oxidizing agent and a stream of reducing agent are sparged.

25

10. Fuel cell according to Claim 9, characterized in that the water is water capable of regenerating the biofilm deposited before the cell is put into operation.

30

11. Fuel cell according to Claim 10, characterized in that the water is circulating water.

35

12. Fuel cell according to Claim 7 or 8, characterized in that the oxidizing agent and the reducing agent feed their respective compartments directly in the form of a gas stream.
- 5
13. Fuel cell according to Claim 12, characterized in that the gas stream or streams feeding the compartment or compartments provided with a biofilm have a moisture content such that it allows the said biofilm to be regenerated.
- 10
14. Fuel cell according to Claim 12, characterized in that a stream of water coexists in parallel with the gas stream or streams feeding the compartment or compartments provided with a biofilm, the said stream of water being intended to regenerate the said biofilm.
- 15
15. Fuel cell according to any one of Claims 7 to 14, characterized in that the electrode (anode and/or cathode) is formed from a material chosen from the group comprising stainless steel and aluminium, nickel or titanium alloys.
- 20
16. Fuel cell according to any one of Claims 7 to 14, characterized in that the oxidizing agent is oxygen and the reducing agent is hydrogen.
- 25
17. Electrode (anode and/or cathode) for a fuel cell, which electrode is coated on at least part of its surface with a biofilm, before it is placed in the said cell, and preferably held in a medium capable of regenerating the biofilm.
- 30

B 14071.3 FG

27

18. Electrode (anode and/or cathode) for which the biofilm is obtained by implementing the process according to any one of Claims 1 to 6.
-

5

**ABSTRACT**

The present invention relates to a process for the treatment of at least one of the electrodes (cathode and/or anode) of a fuel cell, before the said cell is operated and before or after the said electrode is placed in the said cell, consisting in forming a biofilm on at least part of the surface of the said electrode, by immersing the said electrode in a medium capable of causing the growth of biofilms, the said biofilm being intended to catalyse the reaction at the electrode, and consisting simultaneously in subjecting the said electrode to a bias potential.

The invention also relates to a fuel cell comprising at least one electrode covered with a biofilm, obtained before the said electrode is placed in the cell, and to the electrode.